

ISO GROUT PLUS 2030

Product Data Sheet

Description:

ISO GROUT PLUS 2030 is a polymer-rich cementitious tile joint filler. It is a blend of selected cement, graded filler, and selected polymers which when mixed with water forms a durable and tough joint filler that can be used for sealing tile joints.

Uses:

ISO GROUT PLUS can be used to fill the joints of tiles, marbles or granites, for grouting joints from 2 to 15 mm wide.

Advantages:

- ISO GROUT PLUS is water-resistant, crack-free up to 15mm wide joints.
- Available in white & grey. Other colors are available on request.
- Ideal for both interior and exterior use.
- No fading! color is specially formulated with selected pigments so that fading does not take place over a period of time.
- Rigid filler ! it has strong bonding properties so that the grout remains in place permanently without wear.

Technical Properties:

Base :	High grade cement modified with special polymers
Colour :	Grey, White and other colour on request.
Density :	1.8gm/cc
Compressive Strength :	30-35 N/mm ² at 28 Days (30-35 Mpa)
Tensile Strength :	2.75 N mm ² at 28 days (2.75 Mpa)



Application procedure:

Surface preparation

ISO GROUT PLUS can be applied after a minimum of 24 hours from tiling. All tiles should be securely fixed and cleaned before applying ISO GROUT PLUS

Mixing

Mixing can be done using a slow speed drill fitted with a paddle .Approximately 3 to 3.5 liters of water is required for 10 kg of ISO GROUT PLUS. Take measured quantity of water in a container, add ISO GROUT PLUS gradually and mix until a uniform lump free paste like consistency is obtained. For critical areas like swimming pools and other water retaining areas ISO GROUT PLUS modified with ISO BOND S.B.R 1030.

(1 liter ISO BOND S.B.R per 10 kg ISO GROUT PLUS + balance amount of water) is recommended.

Application

Apply Iso grout to the tile joints using a putty blade or scraper. Work the material into the joints and fill the joints completely .Remove the surplus material with a cloth and run a rounded tool along the grout to level it. The product can be used up to 2 hours after mixing.

Standards :

ANSI 118.6 1192, BS 5980



ISOBIT

Coverage:

1 kg of isogROUT is sufficient for grouting joints 28 running meter long, 4mm wide and 3mm deep.

Cleaning:

Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.

Packing:

Available in 10 & 20 kg bags .

Storage:

Store under cover, out of direct sunlight and protect from extreme temperatures. In tropical climates the product must be stored in air-conditioned environment.

Shelf life:

Shelf life is up to 12 months when stored as per recommendations.

Health and Safety:

As with all construction chemical product, caution should be always be exercised. Protective clothing such as gloves and goggles should be worn. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally allowed, do not induce vomiting, but call for medical assistance immediately.

*Prior to each use of any product of ISOBIT, its subsidiaries or affiliates ("ISOBIT"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Datasheet which are available at www.isobitiraq.com or by calling ISOBIT's Technical Service Department at +9647501136936. Nothing contained in any ISOBIT literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each ISOBIT product as set forth in the current product label, Product Data Sheet prior to use of the ISOBIT product. ISOBIT warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL***

T1: +964 750 1136 936.
T2: +964 751 740 1493.
E: info@isobitiraq.com.

ISOBIT for Building Chemicals

www.isobitiraq.com